



牢度性能 Fastness Properties

MH编号 TRADE NAME	牢度性能/Fastness properties					牢度性能/Fastness properties					
	耐光性 Light Fastness	耐迁移/Fastness of Bleeding				耐热性/Heat Stability			耐化学性/Fastness to chemicals		
		漆 Laquer	皂洗 Soap Gel	食用油 Edible Oil	黄油 Butter	150°C 30分钟 150°C 30min	180°C 10分钟 180°C 10min	200°C 1分钟 200°C 1min	3% NaOH 24小时 3% NaOH 24hrs	3% H ₂ O ₂ 24小时 3% H ₂ O ₂ 24hrs	水 24小时 Water 24hrs
MH Yellow 20	6-7	4	5	5	5	A	A	A	A	A	A
MH Yellow 57	6-7	4	5	5	5	A	A	A	A	A	A
MH Yellow KK	6-7	4	5	5	5	A	A	A	A	A	A
MH Orange 09	6-7	4	5	5	5	A	A	A	A	A	A
MH Orange 10	6-7	4-5	5	5	5	A	A	A	A	A	A
MH Red 04	7-8	4	5	5	5	A	A	A	A	A	A
MH Red 06	6-7	4	4-5	4-5	4-5	A	A	A	A	A	A
MH Red 35	6-7	4	4-5	4-5	4-5	A	A	A	A	A	A
MH Red 95	6-7	4	4-5	4-5	4-5	A	A	A	A	A	A
MH Red 10	4-5	3	3-4	3-4	3-4	B	B	A	A	A	A
MH Brown 02	6-7	4	5	5	5	A	A	A	A	A	A
MH Brown 05	6-7	4	5	5	5	A	A	A	A	A	A
MH Blue 03	3-4	3	3-4	3-4	3-4	B	B	C	B	B	A
MH Blue 06	5-6	4	5	5	5	A	B	B	A	A	A
MH Green 20	5-6	4	5	5	5	A	B	B	A	A	A
MH Black 04	7-8	5	5	5	4	A	A	A	A	A	A
MH Black 20	6-7	5	5	5	4	A	A	A	A	A	A
MH Black 56	6-7	5	5	5	4	A	A	A	A	A	A

*耐迁移/Fastness of Bleeding: 1 ~ 5 grade
耐光性/Light Fastness: 1 ~ 8 grade

*耐热性/Heat Stability: A ~ C grade
耐化学性/Fastness of chemicals: A ~ C grade

国内销售:
无锡明辉科技有限公司
地址: 江苏省, 无锡市,
锡山经济开发区,
东北塘芙蓉四路
电话: 0510-8295 1188
传真: 0510-8295 1088
电子信箱: mhchem@mhchem.com

OVERSEA SALES:
WUXI MING HUI INTERNATIONAL TRADING CO., LTD.
ADD: 2608 YINHUI CITY GARDEN,
28 SHENGPING LANE,
WUXI, JIANGSU, P.R.CHINA
TEL: +86 510 8273 7597(12LINES)
FAX: +86 510 8270 9160
E-MAIL: gschem@public1.wx.js.cn